AJACCIO

Nm 4800

COMPOSIZIONE
51% Cotone Pettinato
49% Lana Pettinata

IMPIEGO
Macchine Rettilinee finezza 5 ad 1 capo.

ATTENZIONI PARTICOLARI
I colori non sono solidi alla sovratintura ed al candeggio.

ISTRUZIONI DI LAVAGGIO
Lavare in acqua a 30° con saponi neutri oppure a secco con solventi adatti.
In caso di maglieria rigata con colori forti e contrastanti lavare solo a secco.

CONSIGLI UTILI
L'operazione di roccatura richiede macchinari appositi e particolari, per cui,
se non è indispensabile, consigliamo di non effettuare la riroccatura del filo.
Eventuali differenze di contrasto colore, all'interno della stessa rocca o tra rocche differenti,
sono da considerarsi la caratteristica del filato per la sua particolare costruzione.
Suggeriamo comunque di utilizzare sempre due o piu' guidafili nella lavorazione del filato.
Verificare sempre che il filato sia idoneo all'uso al quale viene destinato.
All'inizio della produzione controllare attentamente i primi teli ed in caso di irregolarità del filato interrompere immediatamente la smacchinatura avvisando l'Ufficio Tecnico, la filatura riconoscerà solo kg. 3 di filato smacchinato ed in nessun caso capi finiti e confezionati.

MINIMI
Quantità minime: richiedere supplementi all'ufficio vendite.

SOLIDITÀ
[Valore medio] in acqua 40°C 4, a secco 4, luce 4
Per colori Fluo H114, H117 le solidità potrebbero avere valori inferiori.

COMPOSITION
51% Combed Cotton
49% Combed Wool

APPLICATION
Flat knitting machines 5 gauge 1 ply.

SPECIAL CARES
Fastness of colours is not sufficient for overdyeing and bleaching.

WASHING INSTRUCTION
Wash in 30° water with neutral soap or dry clean with suitable solvents.
In case of striped knitting dry clean only.

USEFUL INSTRUCTION
The winding operation requires special machines and particular care,
therefore we suggest not to re-wax the yarn unless it is extremely necessary.
Any differences in color contrast, within the same cone or between different cones,
are to be considered the characteristics of the yarn due to its particular construction.
However, we always suggest using two or more yarn guides in yarn processing.
Always ensure that the yarn is suitable for the final end use for which it is intended.
When starting production check knitted panels carefully. If yarn defects are noticed **STOP** knitting immediately, and inform Technical Dept. NO CLAIM will be accepted by spinner for more than 3 kilos of knitted yarn and in no case claims will be accepted on finished garments.

MINIMUM
Minimum quantity: the surcharges have to be required to sales office.

FASTNESS
[Medium figures] water 40°C 4, dry cleaning 4, light 4
For H114, H117, fluorescent colours, fastness values might not reach the above mentioned notes.



feel THE YARN

COTONIFICIO OLCESE FERRARI S.p.A.
Ufficio commerciale: Via Marzaghette, 7 - 25030 Adro [BS] ITALY
Tel. +39 030 7458830 - fax +39 030 7458833
sales.office@olceseferrari.it - www.olceseferrari.it

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
951453.0 CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100