M I L K C O T

SOLID COLOURS

Nm 3/50000 - Nm 4200

C O M P O S I Z I O N E

50% Cotone Organico Pettinato

50% Viscosa Latte

I M P I E G O

Macchine Rettilinee finezza 12/5 ad 1 capo

A T T E N Z I O N I P A R T I C O L A R I

I colori non sono solidi alla sovratintura ed al candeggio.

I S T R U Z I O N I D I L A V A G G I O

Lavare in acqua a 30° con saponi neutri oppure a secco con solventi adatti.

In caso di maglieria rigata con colori forti e contrastanti lavare solo a secco.

C O N S I G L I U T I L I

Questo filato è consigliabile lavorarlo a più guidafili.

Verificare sempre che il filato sia idoneo all'uso al quale viene destinato.

All'inizio della produzione controllare attentamente i primi teli ed in caso di irregolarità del filato interrompere immediatamente la smacchinatura avvisando l'Ufficio Tecnico, la filatura riconoscerà solo kg. 3 di filato smacchinato ed in nessun caso capi finiti e confezionati.

M I N I M I

Quantità minime: richiedere supplementi all'ufficio vendite.

T I N T O R I A

Il filato viene tinto con coloranti reattivi

Le cotte ideali di tintoria sono da richiedersi al nostro ufficio commerciale

---

C O M P O S I T I O N

50% Organic Combed Cotton

50% Milk Viscose

A P P L I C A T I O N

Flat knitting machines 12/5 gauge 1 ply.

S P E C I A L C A R E S

Fastness of colours is not sufficient for overdyeing and bleaching

W A S H I N G I N S T R U C T I O N

Wash in 30° water with neutral soap or dry clean with suitable solvents.

In case of striped knitting dry clean only.

U S E F U L I N S T R U C T I O N

Knitting this yarn with three or more thread guides is recommended.

Always ensure that the yarn is suitable for the final end use for which it is intended.

When starting production check knitted panels carefully. If yarn defects are noticed **STOP** knitting immediately, and inform Technical Dept. NO CLAIM will be accepted by spinner for more than 3 kilos of knitted yarn and in no case claims will be accepted on finished garments.

M I N I M U M

Minimum quantity: the surcharges have to be required to sales office.

D Y E I N G


The yarn is dyed using reactive dyestuff.

The minimu dyeing betches have to be checked the sale office

F A S T N E S S

SOLIDITÀ FASTNESS	ISO	SCARICO SU COTONE DISCHARGE ON COTTON	DEGRADO COLOR CHANGING
LAVAGGIO IN ACQUA 40° C WASHING AT 40° C	105-C06	4	4
LAVAGGIO A SECCO DRY CLEANING	105-D01	4	4
SUDORE ACIDO-ALCALINO ACID-ALKALINE PERSPIRATION	105-E04	4	4
SFREGAMENTO/RUBBING REATTIVI A SECCO / DRY REATTIVI A UMIDO / WET	105-X12	 3 - 4 3 - 4	 4 4
LUCE ARTIFICIALE ARTIFICIAL LIGHT	105-B02	-	4

Note: valori medi / average values



ORGANIC BLENDED content standard

50% OCS organically grown cotton
Certified by ICEA
OCS 0008

feel THE YARN

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
951453-O CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100

COTONIFICIO OLCESE FERRARI S.p.A.

Ufficio commerciale: Via Marzaghette, 7 - 25030 Adro (BS) ITALY

Tel. +39 030 7458830 - fax +39 030 7458833

sales.office@olceseferrari.it - www.olceseferrari.it