
OLCESE

REBORN

REBORN

IL FILATO REBORN È REALIZZATO CON COTONE IMPREZIOSITO DA UNA FIBRA INNOVATIVA E SOSTENIBILE: REFIBRA®

REBORN IS A YARN MADE FROM COTTON ENRICHED BY AN INNOVATIVE AND SUSTAINABLE FIBER: REFIBRA™



Tencel™ Feels so right x REFIBRA™ technology

Refibra® è ideata utilizzando fonti di legno rinnovabili e scarti di cotone riciclati per produrre nuove fibre vergini TENCEL™ Lyocell attraverso un pluripremiato ed efficiente processo di produzione a circuito chiuso. Si tratta della prima fibra cellulosica disponibile in commercio con contenuto di materiale chimico riciclato certificata Recycled Content Standard. Il riciclo chimico di Refibra® permette di mantenere sempre un'elevata qualità del prodotto senza perdita di performance.

UN IMPORTANTE PASSO AVANTI PER CONTRIBUIRE ALL'ECONOMIA CIRCOLARE NEL SETTORE TESSILE

Refibra™ is designed using renewable wood sources and recycled cotton waste to produce new TENCEL™ Lyocell virgin fibers through an award-winning and efficient closed-loop production process. This is the first cellulosic fiber commercially available with recycled content standard certified Recycled Content Standard. The chemical recycling of Refibra™ allows to maintain high product quality without performance loss.

AN IMPORTANT STEP FORWARD TO CONTRIBUTE TO THE CIRCULAR ECONOMY IN THE TEXTILE INDUSTRY

OLCESE

R E B O R N

Ne 20/1 - 24/1 - 30/1 - 36/1 - 40/1 - 50/1 Nm 1/34 - 1/40 - 1/50 - 1/60 - 1/68 - 1/85

60% Cotone - 40% Refibra® Lenzing Compatto



● Ne 30/1 Stock Service

REBORN

Ne 20/1 - 24/1 - 30/1 - 36/1 - 40/1 - 50/1

Nm 1/34 - 1/40 - 1/50 - 1/60 - 1/68 - 1/85

COMPOSIZIONE

60% Cotone - 40% Refibra® Lenzing Compatto

ATTENZIONI PARTICOLARI

I colori non sono solidi alla sovratintura ed al candeggio

In TESSITURA utilizzare il mischiatrama

In MAGLIERIA utilizzare su finezze adeguate

COMPOSITION

60% Cotton - 40% Refibra™ Lenzing Compact Spun

SPECIAL CARES

Colour fastness is not sufficient for overdyeing and bleaching

Weftblend is recommended in weaving

Knit on adequate gauge

INFORMAZIONI TECNICHE / TECHNICAL INFORMATIONS

SOLIDITÀ FASTNESS	ISO	SCARICO SU COTONE DISCHARGE ON COTTON	DEGRADO COLOR CHANGING
LAVAGGIO IN ACQUA 40°C WASHING AT 40°C	105-C06	4	4
LAVAGGIO A SECCO DRY CLEANING	105-D01	4	4
SUDORE ACIDO-ALCALINO ACID-ALKALINE PERSPIRATION	105-E04	4	4
SFREGAMENTO/RUBBING REATTIVI / IDROSOL A SECCO/DRY REATTIVI A UMIDO / WET IDROSOL A UMIDO / WET	105-X12	 3 - 4 3 - 4 2 - 3	 4 4 3
LUCE ARTIFICIALE ARTIFICIAL LIGHT	105-B02	—	4
MERCERIZZO MERCERIZED	—	3	—

NOTE: valori medi / average values



DETOX

Ufficio commerciale: Via Marzaghette, 7 - 25030 Adro (BS) ITALY
Tel. +39 02 2671721 - Fax +39 02 26717233
info@olceseferrari.it - www.olceseferrari.it

OEKO-TEX®
CONFIDENCE IN TEXTILES
STANDARD 100
1108631.0 CENTROCOT
Tested for harmful substances.
www.oeko-tex.com/standard100